

AD-A242 565



Vu

2

TECHNICAL REPORT BRL-TR-3283

# BRL

## TEMPERATURE COMPENSATION TECHNIQUES AND TECHNOLOGIES - AN OVERVIEW

DAVID L. KRUCZYNSKI  
JOHN R. HEWITT

OCTOBER 1991

DTIC  
ELECTE  
NOV 18 1991  
S B D

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION IS UNLIMITED.

U.S. ARMY LABORATORY COMMAND

BALLISTIC RESEARCH LABORATORY  
ABERDEEN PROVING GROUND, MARYLAND

91-15840

91 11-8 070

## **NOTICES**

**Destroy this report when it is no longer needed. DO NOT return it to the originator.**

**Additional copies of this report may be obtained from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Road, Springfield, VA 22161.**

**The findings of this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.**

**The use of trade names or manufacturers' names in this report does not constitute indorsement of any commercial product.**

# UNCLASSIFIED

<b>REPORT DOCUMENT PAGE</b>			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1216 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project(0704-0188), Washington, DC 20503				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE <b>October 1991</b>		3. REPORT TYPE AND DATES COVERED <b>Final, Apr 89 - Apr 90</b>
4. TITLE AND SUBTITLE <b>Temperature Compensation Techniques and Technologies - An Overview</b>			5. FUNDING NUMBERS <b>PR: 1L162618AH80</b>	
6. AUTHOR(S) <b>David L. Kruczynski and John R. Hewitt</b>				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)				
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) <b>USA Ballistic Research Laboratory ATTN: SLCBR-DD-T Aberdeen Proving Ground, MD 21005-5066</b>			8. PERFORMING ORGANIZATION REPORT NUMBER  <b>BRL-TR-3283</b>	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT <b>Approved for Public Release - Distribution is Unlimited</b>			12b. DISTRIBUTION CODE	
<div>13. ABSTRACT (Maximum 200 words)</div> <p>Most current propulsion concepts are designed to operate below optimum performance levels solely because of the need to compensate for temperature sensitivity. Performance at ambient temperature is restricted such that firing under temperature extremes will not exceed system safety limits for pressure. This allows a propulsion concept to perform worldwide in environments ranging from desert to arctic.</p> <p>If a system were available which had little or no temperature sensitivity in practical operating environments (-45 degrees C to 63 degrees C) propulsion concepts could be designed to operate at peak pressure levels through all temperatures. Such system optimization through temperature compensation could achieve significant performance gains.</p> <p>Various concepts have been proposed, suggested, or in a few cases experimentally demonstrated which attempt to achieve temperature compensation. This paper surveys available literature on such concepts and assesses the practicality and performance benefits of each. Concepts addressed include chemical techniques (propellant formulation and use of additives), propellant surface area control, and relatively new volume compensation techniques.</p>				
14. SUBJECT TERMS <b>Temperature Compensating, Pressure Reduction, Performance Increase, Control Tube Primer, Ball Propellant, LOVA, Volume Control, Hypervelocity, Propulsion, Propellants, Temperature</b>			15. NUMBER OF PAGES <b>24</b>	
17. SECURITY CLASSIFICATION OF REPORT <b>UNCLASSIFIED</b>			16. PRICE CODE	
18. SECURITY CLASSIFICATION OF THIS PAGE <b>UNCLASSIFIED</b>		19. SECURITY CLASSIFICATION OF ABSTRACT <b>UNCLASSIFIED</b>		20. LIMITATION OF ABSTRACT <b>SAR</b>

INTENTIONALLY LEFT BLANK.


# TABLE OF CONTENTS

	<u>Page</u>
LIST OF FIGURES .....	v
LIST OF TABLES .....	v
1. INTRODUCTION .....	1
2. THE GROUND RULES AND THEORY .....	3
3. HISTORICAL AND RECENT WORK BY MECHANISM .....	4
3.1 Chemical .....	4
3.2 Surface Area .....	4
3.2.1 LOVA .....	5
3.2.2 Compacted Ball Propellant .....	5
3.3 Volume Control .....	6
3.3.1 Control Tube Device .....	6
3.3.2 Variable Volume Gun Tube .....	8
4. SUMMARY .....	10
5. REFERENCES .....	11
DISTRIBUTION LIST .....	13



<b>Accession For</b>	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

INTENTIONALLY LEFT BLANK.



## LIST OF FIGURES

<u>Figure</u>	<u>Page</u>
1. Real and Ideal Temperature Coefficients .....	2
2. Compacted Ball Propellant Temperature Performance .....	6
3. Control Tube Device Concept .....	7
4. Control Tube Device Firing Data - 120-mm Cannon .....	7
5. Variable Volume Gun Tube Concepts .....	8
6. Variable Volume Experimental Charge .....	9
7. Variable Volume Experimental Data .....	10

## LIST OF TABLES

<u>Table</u>	<u>Page</u>
1. Typical Howitzer Charge Temperature Performance .....	1
2. Typical Tank Charge Temperature Performance .....	2

INTENTIONALLY LEFT BLANK.



## 1. INTRODUCTION

Propulsion systems for conventional gun-based weapon systems are designed to operate safely over a variety of environmental conditions. Extremes of temperature are one of the more important conditions which the propulsion designer must consider when contemplating a new charge design. Global as well as widely varying local climatic conditions generally dictate that a propulsion concept must perform safely at temperature extremes of at least  $-45^{\circ}\text{C}$  to  $+63^{\circ}\text{C}$ .

Meeting these requirements with chemical based propulsion systems has entailed limiting the performance of the system at ambient conditions ( $21^{\circ}\text{C}$ ) so that when the system is fired at high temperatures safety constraints on chamber pressure are not exceeded. Since ambient, or close to ambient, conditions may represent a high percentage of the weapons exposure, it becomes obvious that weapon performance is rarely optimized. In addition, performance at lower temperatures generally degrades further, since the cold temperature pressures are usually lowest. Tables 1 and 2 detail velocity and pressure data for typical tank and howitzer propelling charges. Note that in general, higher pressure systems exhibit higher temperature coefficients.

Table 1. Typical Howitzer Charge Temperature Performance			
<i>155-MM 198 Howitzer Firing M203A1 Charge. System Pressure Limit 405 MPa</i>			
<u>Parameter</u>	<u>Cold</u>	<u>Ambient</u>	<u>Hot</u>
Chamber pressure (MPa)	311	363	394
Velocity (m/s)	782	833	860
<u>Temperature coefficients</u>			
Pressure (MPa/ $^{\circ}\text{C}$ )	-0.72		0.74
Velocity (m/s/ $^{\circ}\text{C}$ )	-0.71		0.64
Percent pressure change from ambient	- 14		9
Percent velocity change from ambient	- 6		3
<i>Cold <math>-51^{\circ}\text{C}</math>, Ambient <math>21^{\circ}\text{C}</math>, Hot <math>63^{\circ}\text{C}</math></i>			

It is obvious that significant performance gains could be realized if the designer could control the changes in propulsion performance with temperature, usually termed velocity and pressure coefficients of temperature. Figure 1 demonstrates graphically the the result of flattening this coefficient.

Reducing temperature coefficients in gun based weapons will be referred to henceforth as temperature compensation techniques or simply temperature compensation. It is the intent of the authors to quickly review past research and then present results from recent inquiries.

Table 2. Typical Tank Charge Temperature Performance

120-MM M256 Cannon Firing M829 Cartridge. System Pressure Limit 670 MPa

<u>Parameter</u>	<u>Cold</u>	<u>Ambient</u>	<u>Hot</u>
Chamber pressure (MPa)	416	526	653
Velocity (m/s)	1535	1675	1768
<u>Temperature Coefficients</u>			
Pressure (MPa/° C)	-1.64		3.02
Velocity (m/s/° C)	-2.09		2.21
Percent pressure change from ambient	- 21		24
Percent velocity change from ambient	- 8		6

*Cold -46 °C, Ambient 21 °C, Hot 63° C*




Figure 1. Real and Ideal Temperature Coefficients

Before addressing the details of past and present attempts to reduce temperature coefficients it is worthwhile to consider the idea of always firing the charge at the hot temperature limit.

Maintaining the ammunition storage areas in tanks and self-propelled artillery at hot temperatures has been discussed for several years. Using this method the charge could always operate at peak performance levels. Should the ammunition heating mechanism not work the charges could still safely be fired since they would perform at normal lower pressure and performance levels when cooled.

There are of course some readily foreseeable problems with this technique. First, the propellant might change performance levels after long periods of high temperature soaking or cycling due to the release of volatiles. Second, without the main power plant of the vehicle operating, a possible scenario for dug-in or concealed operations, there is not likely to be enough power to continue heating the propellant. Finally, many non-powered systems simply may not have the ability for propellant conditioning.

For certain applications, however, the idea seems to have significant merit and is worth further consideration.

## 2. THE GROUND RULES AND THEORY

The primary reason that temperature compensation techniques are difficult to achieve and promote is that by their very nature they are pushing a system to its "upper limits". By that it is meant that attempting to reduce the temperature coefficient of a propulsion system usually entails operation at top pressure levels for ambient conditions with temperature induced changes controlled or mitigated. Should these controls or techniques fail, the weapon system would likely be subjected to unacceptable and unsafe loads. Therefore the temperature compensation technique, whatever design it might take, must be absolutely fail-safe. This limitation is stated at the outset not to discourage examination of the feasibility of such concepts but as a common design constraint that is always present if not explicitly stated in the following discussions.

The variables available to the charge/weapon designer to control temperature related performance are controlled by basic physics starting with the equation of state:

$$P(V - mb) = nRT, \quad (1)$$

where  $P$  = pressure,  $V$  = volume,  $n$  = moles of gas,  $R$  = universal gas constant,  $T$  = temperature,  $m$  = propellant gas mass, and  $b$  = covolume. Rearranging to

$P = \frac{nRT}{(V - mb)}$  reveals the obvious dependency of pressure on available volume.

A projectile being fired from a weapon is somewhat analogous to piston movement in a cylinder in that the force driving the piston/projectile must be carefully controlled such that the cylinder/gun tube is not overloaded. This implies that the rate of pressure generation be balanced at some point (the tube pressure limit) by the generation of additional volume as the projectile moves downbore. The pressurization due to the burning propellant is dependent on the propellant gas mass generation rate as shown in Equation 2:

$$\dot{m} = prS, \quad (2)$$

where  $\dot{m}$  = gas mass generation rate,  $\rho$  = propellant density,  $r$  = propellant burning rate and  $S$  = propellant surface area available. The propellant burning rate ( $r$ ) is largely a function of chemical kinetics.

In summary, the controlling factors affecting ultimate pressure in a gun tube during firing are the volume available during the combustion cycle, the rate at which the propellant burns (largely controlled by its chemical make-up), and the amount of propellant surface area available at any point in the combustion process.

### 3. HISTORICAL AND RECENT WORK BY CONTROLLING MECHANISM

A literature study of temperature sensitivity related research was conducted (Copenhagen, McCarty, and Hughes 1980; Foster and Miller 1980; Graham and Martin 1975; Hamner, Hightower and Rector 1978; Jones, Foster, and Miller 1981; Corley and Kobbe-man 1981; Palm 1983; Booth and Stokes 1986; Cohen and Flanigan 1983, 1984; Lyles, Flanigan and Askins 1971; Beardell and White 1982; Christian 1982; White et al. 1982; Stiefel 1983). The reported research generally address two generic modes by which temperature sensitivity is produced, or controlled.

#### 3.1. Chemical

The first and the most extensively researched mode involves chemical make-up and propellant chemistry interactions. These studies, which focus primarily on solid fuel rocket motors, have had some success controlling temperature sensitivity through the use of additives such as aluminum, lead, copper, iron oxide, and others. These additives appear to lower temperature sensitivities at low pressures generally below 20 MPa. Attempts to control temperature sensitivity at higher pressures through the use of additives have generally met with little success. Since most gun systems operate in the 345 - 620 MPa range there has been no real success with this approach in guns and thus this option is not further addressed in this paper.

Deterrents have been used to retard excessively rapid burning or tailor performance of some propellant geometries. Their role in temperature coefficient reduction is unclear and undergoing continued study (Gonzalez and Worthington 1989; Anderson and Puhalla 1989). Deterrents may prove to be required to make use of propellant geometries which might otherwise be ballistically unacceptable, yet may have desirable temperature compensation properties through control of surface availability during combustion, such as ball propellant geometries.

#### 3.2. Surface Area

Control of surface area available during the combustion process has been studied for many years as a solution to offset the natural tendency of any energetic material to change performance as a function of temperature. These studies generally center on

control of surface generation as dictated by the mechanical properties of the grain or charge. The rationale for this approach follows:

- *At high temperatures the propellant may become pliable and during the pressurization process collapse inward to fill voids such as perfs. This occlusion process would in effect reduce the available surface area for combustion, thus reducing the rate of pressurization and most likely the peak pressure obtained.*
- *Under cold conditions the propellant may become brittle and break apart more readily during the combustion process producing additional surface area for burning and thus raising the pressure.*
- *For compacted charges the effect of cold temperatures is generally to produce quicker deconsolidation, additional grain surface area for burning, and a resultant increase in pressure. At hot temperatures the inverse occurs which reduces the grains exposed and lowers the pressure.*

Note that these control mechanisms may be counter-productive to each other. For instance, formulation changes to make a propellant more pliable at hot temperature are likely to make it less brittle at cold temperatures and vice versa. In addition care must be taken when working in the cold regime to not let the propellant become excessively brittle as this can lead to overly high increases in pressure should the available additional surface become too large.


Some specific examples of mechanical properties and surface control include recent low vulnerability propellants (LOVA) and compacted ball charges. These are further discussed below.

### 3.2.1. LOVA

During the development of High Energy LOVA Propellants reduced temperature coefficients relative to non-LOVA propellants were encountered. For instance for some LOVA formulations a hot temperature coefficient of 1.73 MPa per degree C was noted (Rocchio, personal communication 1989). Note that high energy non-LOVA propellants such as JA2 may have hot temperature coefficients as high as 3.11 MPa per degree C. It is believed that this reduced temperature coefficient is a result of surface area availability via one of the mechanisms noted above. LOVA temperature sensitivity is under continuing study.

### 3.2.2. Compacted Ball Propellant

Compacted ball propellant charges used in several medium caliber charges (20 and 30 mm) display favorable temperature compensation performance. Figure 2 demonstrates these results.




The mechanism involved in temperature compensation for compacted ball propellants is believed to be quite complex. This is due to the fact that the propellant balls are generally first coated with a deterrent coating of varying thickness depending upon application. Then they are rolled to change their geometry from that of a ball to that of an oblate sphere, which may induce fissures in the propellant surface. Finally they are compressed at high pressures to form a solid compacted block of propellant. The contributions of each process in reducing the temperature coefficient by surface control is not entirely clear and is undergoing extensive scrutiny. It does appear however that the compaction of the balls plays a key role in reducing the low temperature coefficient. For instance the compacted charge appears to deconsolidate at a much higher, but controlled, rate cold than ambient or hot (Gonzalez and Worthington 1989; Anderson and Puhalla 1989).

### 3.3. Volume Control

Recent temperature compensation research has centered around the third available mechanism to reduce temperature sensitivity, volume control, defined as the ability to control the initial free volume in a weapon chamber as a function of the propelling charge temperature. As detailed earlier the available volume during the combustion process directly effects the achieved peak pressure. Two such studies are detailed below.

#### 3.3.1. Control Tube Device


A control tube device has the ability to adjust the position of the projectile prior to igniting the main charge. This allows it to increase the effective chamber volume for a hot



propellant by moving the projectile forward just prior to igniting the charge itself. Figure 3 displays this concept in its generic form.

Recent firings of such a device demonstrated that this concept is feasible. Figure 4 shows some of these results.

Control tube concepts can be relatively complex in design. In addition, the fail-safe features of such devices remain to be proven.



### 3.3.2. Variable Volume Gun Tube


A concept currently under study by the author involves modifying the gun tube itself so that, in its ideal form, it is capable of adjusting the chamber volume of the weapon to neutralize the effects of temperature sensitivity.

This concept has several advantages over previously discussed techniques. First, it is relatively charge independent, meaning that the same mechanism would be able to correct for various charges, regardless of their peak performance or relative temperature sensitivities. This would solve many problems associated not only with varying performances of different type charges but with changes within lots of the same type charges.

Secondly, it would be capable of adjusting volume both up and down and could achieve true flat temperature sensitivity performance across any desirable range of temperatures. Finally the concept could be applied across a variety of weapons of quite different sizes and specifications.

How might such a system work? It might vary in complexity from a simple variable intrusion breech set by the soldier from sensor information in the charge stowage area, e.g., approximate charge temperature, to a smart chamber which is capable of sensing pressure rise rates and instantaneously adjusting chamber volume. In between these possibilities might be systems which employ barcode-like temperature sensors on charge components which are read just before or during charge insertion and either prompt the user to reset the chamber volume or communicate with an automated system to do it for him. Figure 5 displays two potential design concepts.

To explore the feasibility of such a concept a simple experiment was performed. The basic goal of this experiment was to determine what change in volume might be required to implement such a system.






Since a variable chamber volume system was not yet available a simple inverse compensation experiment was designed. In this experiment a charge was designed which was somewhat less than full chamber bore in size. Several of these charges were fired hot ( $63^{\circ}\text{C}$ ) while chamber pressures and velocities were recorded. Then the same charge design was fired at ambient temperatures with full bore length spacers (volume compensators) inserted in the chamber. The procedure was repeated with increasingly larger spacers in an attempt to achieve the pressures obtained in the hot firings. It was felt that to a reasonable approximation this technique could be related to one for a expandable chamber system.

Several views of the test charges used are shown in Figure 6. Pressure increase versus volume decrease results as compared to the baseline hot charge case are shown in Figure 7.

Extrapolating the results of Figure 7 it can be seen that for this system a decrease of 18 percent in volume is required to reproduce the temperature induced pressure change which occurs during the hot firing. While this might on first look appear to be a considerable



Figure 6. Variable Volume Experimental Charge



volume change requirement, it should be noted that it could be obtained by a full bore axial length change of only 15 cm or a full chamber radial change of just 1.34 cm.

Future work in this area will concentrate on engineering prototype volume compensation hardware, most probably a variable intrusion breech. While the efforts in volume compensation for temperature sensitivity reduction are still in their infancy, it is a promising technique for increasing the performance of current conventional based propulsion systems.

#### 4. SUMMARY

Chemical modification of propellant to reduce temperature sensitivity has to date met with success with only low pressure propulsion systems such as rocket motors. Temperature compensation through control of propellant mechanical properties and therefore surface availability has met with limited success in small to medium caliber systems to date. There seems to be no physical reason why these mechanisms cannot be reproducibly controlled and scaled up. However it is still unclear if these mechanisms can be made to work well at both ends of the temperature spectrum simultaneously. Volume control techniques are still in their infancy but hold the promise of a charge independent, broad temperature range solution.

## 5. REFERENCES

- Anderson, R.D. and R.T. Puhalla. "Parametric Study Of Temperature Sensitivity Of Ball Propellants." Proceedings of the 26th JANNAF Combustion Meeting, CPIA Publication 529, vol. III, pp. 395-406, October 1989.
- Beardell, A.J. and K.J. White. "Workshop Report: Temperature Sensitivity Of Gun Propellants." Proceedings of the 19th JANNAF Combustion Meeting, CPIA Publication 366, vol. I, pp. 473-480, October 1982.
- Booth, D.W. and B.B. Stokes. "Temperature Sensitivity Of Reduced Smoke HTPB Propellant." Proceedings of the 1986 JANNAF Propulsion Meeting, CPIA Publication 455, vol. III, pp. 525-534, August 1986.
- Christian, T.W. "Temperature Sensitivity Of Gun Propelling Charges." CPTR 82-18, Johns Hopkins University Applied Physics Laboratory, Laurel, Maryland, November 1982.
- Cohen, N.S. and D.A. Flanigan. "Effects Of Propellant Formulation On Burn Rate-Temperature Sensitivity, A Review." Proceedings of the 1984 JANNAF Propulsion Meeting, CPIA Publication 390, vol. III, pp. 243-262, February 1984.
- Cohen, N.S. and D.A. Flanigan. "Procedures In The Determination Of  $\Pi_k$ ." Proceedings of the 20th JANNAF Combustion Meeting, CPIA Publication 383, vol. II, pp. 69-78, October 1983.
- Copenhafer, R.A., K.P. McCarty, and C.W. Hughes. "The Influence Of Formulation Variables On The Ballistic Temperature Sensitivity Of High Performance (Class 1.1) Aluminized Propellants." Proceedings of the 17th JANNAF Combustion Meeting, CPIA Publication 329, vol. IV, pp. 17-31, November 1980.
- Corley, B.M. and D.D. Kobbeman. "High Burn Rate/Low Exponent Propellants For Missile Application." Proceedings of the 1981 JANNAF Propulsion Meeting, CPIA Publication 340, vol. VIII, pp. 371-386, May 1981.
- Foster, R.L. and R.R. Miller. "The Burn Rate Temperature Sensitivity Of Aluminized And Non-aluminized HTPB Propellants." Proceedings of the 1980 JANNAF Propulsion Meeting, CPIA Publication 315, vol. IV, pp. 667-693, April 1980.
- Gonzalez, A. and D. Worthington. "Ball Propellants And Temperature Compensation: A Combustion Study." Proceedings of the 26th JANNAF Combustion Meeting, CPIA Publication 529, vol. I, pp. 317-324, October 1989.
- Graham, P.H. and J.D. Martin. "Development And Evaluation Of Wired End Burning Propellant For Air Launched Missiles." Proceedings of the 1974 JANNAF Propulsion Meeting, CPIA Publication 260, vol. III, part 2, pp. 957-978, January 1975.

Hamner, J.W., J.O. Hightower, and C.M. Rector. "Summary Of Propellant Development Effort For ASALM Integral Ramjet Booster." Proceedings of the 1978 JANNAF Propulsion Meeting, CPIA Publication 293, vol. I, pp. 421-465, February 1978.

Jones, M.L., R.L. Foster, and R.R. Miller. "Effect Of Temperature On Ballistics Of HTPB Propellants." Proceedings of the 1981 JANNAF Propulsion Meeting, CPIA Publication 340, vol. IV, pp. 64-80, May 1981.

Lyles, B.J., D.A. Flanigan, and R.E. Askins. "Temperature Sensitivity Of Composite Propellants: A Thermodynamic/Data Correction Approach." Proceedings of the 8th JANNAF Combustion Meeting, CPIA Publication 220, vol. II, pp. 91-120, November 1971.

Palm, E.J. "Ballistic Variability Of Minimum Signature Rocket Motors." Proceedings of the 1983 JANNAF Propulsion Meeting, CPIA Publication 370, vol. IV, pp. 555-589, February 1983.

Rocchio, Joseph J., Personal communication with author. US Army Ballistic Research Laboratory, October 18, 1989.

Stiefel, L. "Charge Design Studies For A Cannon Caliber APDS Round." Proceedings of the 1983 JANNAF Propulsion Meeting, CPIA Publication 370, vol. III, pp. 229-239, February 1983.

White, K.J., D.C. Mann, A.W. Horst, and R.J. Lieb. "Chemical And Physical Studies Related To Propellant Temperature Sensitivity." Proceedings of the 19th JANNAF Combustion Meeting, CPIA Publication 366, vol. I, pp. 481-489, October 1982.

No. of  
Copies Organization

- 2 Administrator  
Defense Technical Info Center  
ATTN: DTIC-DDA  
Cameron Station  
Alexandria, VA 22304-6145
- 1 Commander  
U.S. Army Materiel Command  
ATTN: AMCDRA-ST  
5001 Eisenhower Avenue  
Alexandria, VA 22333-0001
- 1 Commander  
U.S. Army Laboratory Command  
ATTN: AMSLC-DL  
2800 Powder Mill Road  
Adelphi, MD 20783-1145
- 2 Commander  
U.S. Army Armament Research,  
Development, and Engineering Center  
ATTN: SMCAR-IMI-I  
Picatinny Arsenal, NJ 07806-5000
- 2 Commander  
U.S. Army Armament Research,  
Development, and Engineering Center  
ATTN: SMCAR-TDC  
Picatinny Arsenal, NJ 07806-5000
- 1 Director  
Benet Weapons Laboratory  
U.S. Army Armament Research,  
Development, and Engineering Center  
ATTN: SMCAR-CCB-TL  
Watervliet, NY 12189-4050
- (Unclass. only) 1 Commander  
U.S. Army Armament, Munitions  
and Chemical Command  
ATTN: AMSMC-IMF-L  
Rock Island, IL 61299-5000
- 1 Director  
U.S. Army Aviation Research  
and Technology Activity  
ATTN: SAVRT-R (Library)  
M/S 219-3  
Ames Research Center  
Moffett Field, CA 94035-1000

No. of  
Copies Organization

- 1 Commander  
U.S. Army Missile Command  
ATTN: AMSMI-RD-CS-R (DOC)  
Redstone Arsenal, AL 35898-5010
- 1 Commander  
U.S. Army Tank-Automotive Command  
ATTN: ASQNC-TAC-DIT (Technical  
Information Center)  
Warren, MI 48397-5000
- 1 Director  
U.S. Army TRADOC Analysis Command  
ATTN: ATRC-NSR  
White Sands Missile Range, NM 88002-5502
- 1 Commandant  
U.S. Army Field Artillery School  
ATTN: ATSF-CSI  
Ft. Sill, OK 73503-5000
- (Class. only) 1 Commandant  
U.S. Army Infantry School  
ATTN: ATSH-CD (Security Mgr.)  
Fort Benning, GA 31905-5660
- (Unclass. only) 1 Commandant  
U.S. Army Infantry School  
ATTN: ATSH-CD-CSG-OR  
Fort Benning, GA 31905-5660
- 1 Air Force Armament Laboratory  
ATTN: WL/MNOI  
Eglin AFB, FL 32542-5000
- Aberdeen Proving Ground
- 2 Dir, USAMSAA  
ATTN: AMXSY-D  
AMXSY-MP, H. Cohen
- 1 Cdr, USATECOM  
ATTN: AMSTE-TC
- 3 Cdr, CRDEC, AMCCOM  
ATTN: SMCCR-RSP-A  
SMCCR-MU  
SMCCR-MSI
- 1 Dir, VLAMO  
ATTN: AMSLC-VL-D
- 10 Dir, BRL  
ATTN: SLCBR-DD-T

No. of  
Copies Organization

- 1 Commander  
U.S. Army Concepts Analysis Agency  
ATTN: D. Hardison  
8120 Woodmont Ave.  
Bethesda, MD 20014
- 1 C.I.A.  
01R/DB/Standard  
Washington, DC 20505
- 1 Director  
U.S. Army Ballistic Missile  
Defense Systems Command  
Advanced Technology Center  
P. O. Box 1500  
Huntsville, AL 35807-3801
- 1 Chairman  
DOD Explosives Safety Board  
Room 856-C  
Hoffman Bldg. 1  
2461 Eisenhower Ave.  
Alexandria, VA 22331-0600
- 1 Commander  
U.S. Army Materiel Command  
ATTN: AMCDE-DW  
5001 Eisenhower Ave.  
Alexandria, VA 22333-5001
- 1 Department of the Army  
Office of the Product Manager  
155mm Howitzer, M109A6, Paladin  
ATTN: SFAE-AR-HIP-IP, Mr. R. De Kleine  
Picatinny Arsenal, NJ 07806-5000
- 2 Commander  
Production Base Modernization Agency  
U.S. Army Armament Research,  
Development, and Engineering Center  
ATTN: AMSMC-PBM, A. Siklosi  
AMSMC-PBM-E, L. Laibson  
Picatinny Arsenal, NJ 07806-5000

No. of  
Copies Organization

- 3 PEO-Armaments  
Project Manager  
Tank Main Armament Systems  
ATTN: AMCPM-TMA, K. Russell  
AMCPM-TMA-105  
AMCPM-TMA-120, C. Roller  
Picatinny Arsenal, NJ 07806-5000
- 15 Commander  
U.S. Army Armament Research,  
Development, and Engineering Center  
ATTN: SMCAR-AEE  
SMCAR-AEE-B,  
A. Beardell  
D. Downs  
S. Einstein  
S. Westley  
S. Bernstein  
J. Rutkowski  
B. Brodman  
P. Bostonian  
R. Cirincione  
A. Grabowsky  
P. Hui  
J. O'Reilly  
N. Ross  
SMCAR-AES, S. Kaplowitz, Bldg. 321  
Picatinny Arsenal, NJ 07806-5000
- 2 Commander  
U.S. Army Armament Research,  
Development, and Engineering Center  
ATTN: SMCAR-CCD, D. Spring  
SMCAR-CCH-V, C. Mandala  
Picatinny Arsenal, NJ 07806-5000
- 1 Commander  
U.S. Army Armament Research,  
Development, and Engineering Center  
ATTN: SMCAR-HFM, E. Barriores  
Picatinny Arsenal, NJ 07806-5000
- 1 Commander  
U.S. Army Armament Research,  
Development, and Engineering Center  
ATTN: SMCAR-FSA-T, M. Salisbury  
Picatinny Arsenal, NJ 07806-5000

**No. of  
Copies Organization**

- 1 Commander, USACECOM  
R&D Technical Library  
ATTN: ASQNC-ELC-IS-L-R, Myer Center  
Fort Monmouth, NJ 07703-5301
- 1 Commander  
U.S. Army Harry Diamond Laboratories  
ATTN: SLCHD-TA-L  
2800 Powder Mill Rd.  
Adelphi, MD 20783-1145
- 1 Commandant  
U.S. Army Aviation School  
ATTN: Aviation Agency  
Fort Rucker, AL 36360
- 2 Program Manager  
U.S. Tank-Automotive Command  
ATTN: AMCPM-ABMS, T. Dean (2 cy)  
Warren, MI 48092-2498
- 1 Program Manager  
U.S. Tank-Automotive Command  
Fighting Vehicles Systems  
ATTN: AMCPM-BFVS  
Warren, MI 48092-2498
- 1 President  
U.S. Army Armor & Engineer Board  
ATTN: ATZK-AD-S  
Fort Knox, KY 40121
- 1 Project Manager  
U.S. Army Tank-Automotive Command  
M-60 Tank Development  
ATTN: AMCPM-ABMS  
Warren, MI 48092-2498
- 1 Director  
HQ, TRAC RPD  
ATTN: ATCD-MA  
Fort Monroe, VA 23651-5143
- 2 Director  
U.S. Army Materials Technology  
Laboratory  
ATTN: SLCMT-ATL (2 cy)  
Watertown, MA 02172-0001

**No. of  
Copies Organization**

- 1 Commander  
U.S. Army Research Office  
ATTN: Technical Library  
P.O. Box 12211  
Research Triangle Park, NC 27709-2211
- 1 Commander  
U.S. Army Belvoir Research and  
Development Center  
ATTN: STRBE-WC  
Fort Belvoir, VA 22060-5006
- 1 Director  
U.S. Army TRAC-Ft. Lee  
ATTN: ATRC-L, Mr. Cameron  
Fort Lee, VA 23801-6140
- 1 Commandant  
U.S. Army Command and General  
Staff College  
Fort Leavenworth, KS 66027
- 1 Commandant  
U.S. Army Special Warfare School  
ATTN: Rev and Trng Lit Div  
Fort Bragg, NC 28307
- 3 Commander  
Radford Army Ammunition Plant  
ATTN: SMCAR-QA/HI LIB (3 cps)  
Radford, VA 24141-0298
- 1 Commander  
U.S. Army Foreign Science and  
Technology Center  
ATTN: AMXST-MC-3  
220 Seventh Street, NE  
Charlottesville, VA 22901-5396
- 2 Commander  
Naval Sea Systems Command  
ATTN: SEA 62R  
SEA 64  
Washington, DC 20362-5101
- 1 Commander  
Naval Air Systems Command  
ATTN: AIR-954-Technical Library  
Washington, DC 20360

**No. of  
Copies Organization**

- 1 Assistant Secretary of the Navy  
(R, E, and S)  
ATTN: R. Reichenbach  
Room 5E787  
Pentagon Bldg.  
Washington, DC 20375
- 1 Naval Research Laboratory  
Technical Library  
Washington, DC 20375
- 2 Commandant  
U.S. Army Field Artillery Center  
and School  
ATTN: ATSF-CO-MW, E. Dublisky (2 cps)  
Fort Sill, OK 73503-5600
- 1 Office of Naval Research  
ATTN: Code 473, R. S. Miller  
800 N. Quincy Street  
Arlington, VA 22217-9999
- 3 Commandant  
U.S. Army Armor School  
ATTN: ATZK-CD-MS, M. Falkovitch (3 cps)  
Armor Agency  
Fort Knox, KY 40121-5215
- 2 Commander  
U.S. Naval Surface Warfare Center  
ATTN: J. P. Consaga  
C. Gotzmer  
Indian Head, MD 20640-5000
- 4 Commander  
Naval Surface Warfare Center  
ATTN: Code 240, S. Jacobs  
Code 730  
Code R-13,  
K. Kim  
R. Bernecker  
Silver Spring, MD 20903-5000
- 2 Commanding Officer  
Naval Underwater Systems Center  
ATTN: Code 5B331, R. S. Lazar  
Technical Library  
Newport, RI 02840

**No. of  
Copies Organization**

- 5 Commander  
Naval Surface Warfare Center  
ATTN: Code G33,  
J. L. East  
W. Burrell  
J. Johnson  
Code G23, D. McClure  
Code DX-21 Technical Library  
Dahlgren, VA 22448-5000
- 3 Commander  
Naval Weapons Center  
ATTN: Code 388, C. F. Price  
Code 3895, T. Parr  
Information Science Division  
China Lake, CA 93555-6001
- 1 OSD/SDIO/IST  
ATTN: Dr. Len Caveny  
Pentagon  
Washington, DC 20301-7100
- 3 Commander  
Naval Ordnance Station  
ATTN: T. C. Smith  
D. Brooks  
Technical Library  
Indian Head, MD 20640-5000
- 1 AL/TSTL (Technical Library)  
ATTN: J. Lamb  
Edwards AFB, CA 93523-5000
- 1 AFATL/DLYV  
Eglin AFB, FL 32542-5000
- 1 AFATL/DLXP  
Eglin AFB, FL 32542-5000
- 1 AFATL/DLJE  
Eglin AFB, FL 32542-5000
- 1 NASA/Lyndon B. Johnson Space Center  
ATTN: NHS-22 Library Section  
Houston, TX 77054



**No. of  
Copies Organization**

- 1 AFELM, The Rand Corporation  
ATTN: Library D  
1700 Main Street  
Santa Monica, CA 90401-3297
  
- 3 AAI Corporation  
ATTN: J. Hebert  
J. Frankle  
D. Cleveland  
P.O. Box 126  
Hunt Valley, MD 21030-0126
  
- 2 Aerojet Solid Propulsion Company  
ATTN: P. Micheli  
L. Torreyson  
Sacramento, CA 96813
  
- 1 Atlantic Research Corporation  
ATTN: M. King  
5390 Cherokee Ave.  
Alexandria, VA 22312-2302
  
- 3 AL/LSCF  
ATTN: J. Levine  
L. Quinn  
T. Edwards  
Edwards AFB, CA 93523-5000
  
- 1 AVCO Everett Research Laboratory  
ATTN: D. Stickler  
2385 Revere Beach Parkway  
Everett, MA 02149-5936
  
- 2 Calspan Corporation  
ATTN: C. Murphy (2 cps)  
P.O. Box 400  
Buffalo, NY 14225-0400
  
- 1 General Electric Company  
Tactical Systems Department  
ATTN: J. Mandzy  
100 Plastics Ave.  
Pittsfield, MA 01201-3698
  
- 1 IITRI  
ATTN: M. J. Klein  
10 W. 35th Street  
Chicago, IL 60616-3799

**No. of  
Copies Organization**

- 1 Hercules, Inc.  
Allegheny Ballistics Laboratory  
ATTN: William B. Walkup  
P.O. Box 210  
Rocket Center, WV 26726
  
- 1 Hercules, Inc.  
Radford Army Ammunition Plant  
ATTN: E. Hibshman  
Radford, VA 24141-0299
  
- 3 Director  
Lawrence Livermore National  
Laboratory  
ATTN: L-355,  
A. Buckingham  
M. Finger  
L-324, M. Constantino  
P.O. Box 808  
Livermore, CA 94550-0622
  
- 1 Olin Corporation  
Badger Army Ammunition Plant  
ATTN: F. E. Wolf  
Baraboo, WI 53913
  
- 3 Olin Ordnance  
ATTN: E. J. Kirschke  
A. F. Gonzalez  
D. W. Worthington  
P.O. Box 222  
St. Marks, FL 32355-0222
  
- 1 Paul Gough Associates, Inc.  
ATTN: Dr. Paul S. Gough  
1048 South Street  
Portsmouth, NH 03801-5423
  
- 1 Physics International Company  
ATTN: Library, H. Wayne Wampler  
2700 Merced Street  
San Leandro, CA 98457-5602
  
- 1 Princeton Combustion Research  
Laboratory, Inc.  
ATTN: M. Summerfield  
475 U.S. Highway One  
Monmouth Junction, NJ 08852-9650

**No. of  
Copies Organization**

- 2 Rockwell International  
Rocketdyne Division  
ATTN: BA08,  
J.E. Flanagan  
J. Gray  
6633 Canoga Ave.  
Canoga Park, CA 91303-2703
- 1 Thiokol Corporation  
Huntsville Division  
ATTN: Technical Library  
Huntsville, AL 35807
- 1 Sverdrup Technology, Inc.  
ATTN: Dr. John Deur  
2001 Aerospace Parkway  
Brook Park, OH 44142
- 2 Thiokol Corporation  
Elkton Division  
ATTN: R. Biddle  
Technical Library  
P.O. Box 241  
Elkton, MD 21921-0241
- 1 Veritay Technology, Inc.  
ATTN: E. Fisher  
4845 Millersport Highway  
East Amherst, NY 14501-0305
- 1 Universal Propulsion Company  
ATTN: H. J. McSpadden  
Black Canyon Stage 1  
Box 1140  
Phoenix, AZ 84029
- 1 Battelle  
ATTN: TACTEC Library, J.N. Huggins  
505 King Ave.  
Columbus, OH 43201-2693
- 1 Brigham Young University  
Department of Chemical Engineering  
ATTN: M. Beckstead  
Provo, UT 84601

**No. of  
Copies Organization**

- 1 California Institute of Technology  
204 Karman Laboratory  
Main Stop 301-46  
ATTN: F.E.C. Culick  
1201 E. California Street  
Pasadena, CA 91109
- 1 California Institute of Technology  
Jet Propulsion Laboratory  
ATTN: L. D. Strand, MS 512/102  
4800 Oak Grove Drive  
Pasadena, CA 91109-8099
- 1 University of Illinois  
Department of Mechanical/Industrial  
Engineering  
ATTN: H. Krier  
144 MEB; 1206 N. Green Street  
Urbana, IL 61801-2978
- 1 University of Massachusetts  
Department of Mechanical Engineering  
ATTN: K. Jakus  
Amherst, MA 01002-0014
- 1 University of Minnesota  
Department of Mechanical Engineering  
ATTN: E. Fletcher  
Minneapolis, MN 55414-3368
- 3 Georgia Institute of Technology  
School of Aerospace Engineering  
ATTN: B.T. Zinn  
E. Price  
W.C. Strahle  
Atlanta, GA 30332
- 1 Institute of Gas Technology  
ATTN: D. Gidaspow  
3424 S. State Street  
Chicago, IL 60616-3896
- 1 Johns Hopkins University  
Applied Physics Laboratory  
Chemical Propulsion  
Information Agency  
ATTN: T. Christian  
Johns Hopkins Road  
Laurel, MD 20707-0690

**No. of  
Copies** **Organization**

- 1 Massachusetts Institute of Technology  
Department of Mechanical Engineering  
ATTN: T. Toong  
77 Massachusetts Ave.  
Cambridge, MA 02139-4307
- 1 Pennsylvania State University  
Applied Research Laboratory  
ATTN: G. M. Faeth  
University Park, PA 16802-7501
- 1 Pennsylvania State University  
Department of Mechanical Engineering  
ATTN: K. Kuo  
University Park, PA 16802-7501
- 1 Purdue University  
School of Mechanical Engineering  
ATTN: J. R. Osborn  
TSPC Chaffee Hall  
West Lafayette, IN 47907-1199
- 1 SRI International  
Propulsion Sciences Division  
ATTN: Technical Library  
333 Ravenwood Ave.  
Menlo Park, CA 94025-3493
- 1 Rensselaer Polytechnic Institute  
Department of Mathematics  
Troy, NY 12181
- 2 Director  
Los Alamos Scientific Laboratory  
ATTN: T3, D. Butler  
M. Division, B. Craig  
P.O. Box 1663  
Los Alamos, NM 87544
- 1 General Applied Sciences Laboratory  
ATTN: J. Erdos  
77 Raynor Ave.  
Ronkonkoma, NY 11779-6649
- 1 Battelle PNL  
ATTN: Mr. Mark Garnich  
P.O. Box 999  
Richland, WA 99352

**No. of  
Copies** **Organization**

- 1 Stevens Institute of Technology  
Davidson Laboratory  
ATTN: R. McAlevy, III  
Castle Point Station  
Hoboken, NJ 07030-5907
- 1 Rutgers University  
Department of Mechanical and  
Aerospace Engineering  
ATTN: S. Temkin  
University Heights Campus  
New Brunswick, NJ 08903
- 1 University of Southern California  
Mechanical Engineering Department  
ATTN: CHE200, M. Gerstein  
Los Angeles, CA 90089-5199
- 2 University of Utah  
Department of Chemical Engineering  
ATTN: A. Baer  
G. Flandro  
Salt Lake City, UT 84112-1194
- 1 Washington State University  
Department of Mechanical Engineering  
ATTN: C. T. Crowe  
Pullman, WA 99163-5201
- 1 Alliant Techsystems, Inc.  
ATTN: R. E. Tompkins  
MN38-3300  
5700 Smetana Drive  
Minnetonka, MN 55343
- 1 Science Applications, Inc.  
ATTN: R. B. Edelman  
23146 Cumorah Crest Drive  
Woodland Hills, CA 91364-3710
- 1 Battelle Columbus Laboratories  
ATTN: Mr. Victor Levin  
505 King Ave.  
Columbus, OH 43201-2693

**No. of  
Copies    Organization**

- 1    Allegheny Ballistics Laboratory  
Propulsion Technology Department  
Hercules Aerospace Company  
ATTN: Mr. Thomas F. Farabaugh  
P.O. Box 210  
Rocket Center, WV 26726
  
- 1    MBR Research Inc.  
ATTN: Dr. Moshe Ben-Reuven  
601 Ewing St., Suite C-22  
Princeton, NJ 08540
  
- 1    Commander  
Defense Advanced Research Projects Agency  
ATTN: MAJ R. Lundberg  
1400 Wilson Blvd.  
Arlington, VA 22209
  
- 1    U.S. Army Space Technology and Research  
Office  
ATTN: COL D. S. Jackson  
5321 Riggs Road  
Gaithersburg, MD 20882
  
- 1    AFOSR/NA  
ATTN: Dr. J. Tishkoff  
Bolling AFB, DC 20332-6448
  
- 1    Director  
NASA Langley Research Center  
ATTN: Technical Library  
Langley Station  
Hampton, VA 23665
  
- 2    Director  
NASA Langley Research Center  
ATTN: Mail Stop 408,  
W. Scallion  
R. Witcofski  
Langley Station  
Hampton, VA 23665
  
- 1    Director  
Sandia National Laboratories  
ATTN: W. Oberkamp  
Division 1636  
Albuquerque, NM 87185

**No. of  
Copies    Organization**

- 1    Advanced Projects Research, Inc.  
ATTN: Dr. J. Humphrey  
Suite A  
5301 N. Commerce Ave.  
Moorpark, CA 93021
  
- 1    Aerospace Corporation  
Aero-Engineering Subdivision  
ATTN: Walter F. Reddall  
El Segundo, CA 92045
  
- 2    Olin Rocket Research Company  
ATTN: A. Harvey  
11441 Willows Road, NE  
P.O. Box 97009  
Redmond, WA 98073-9709
  
- 4    Naval Research Laboratory  
ATTN: Dr. K. Keilasanath  
Dr. C. Li  
Dr. J. Boris  
Dr. E. Oran  
Washington, DC 20375-5000
  
- 1    Amtec Engineering, Inc.  
P.O. Box 3633  
Bellevue, WA 98009-3633
  
- Aberdeen Proving Ground
  
- 1    Cdr, CSTA  
ATTN: STECS-PO. R. Hendricksen

**No. of  
Copies Organization**

**2     Institut Saint-Louis  
      ATTN: Dr. E. Sellaer  
           Dr. Smeets  
      F 68301 Saint-Louis Cedex  
      12 rue de l'industrie, B.P. 301  
      France**

INTENTIONALLY LEFT BLANK.

## USER EVALUATION SHEET/CHANGE OF ADDRESS

This laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers below will aid us in our efforts.

1. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) \_\_\_\_\_  
\_\_\_\_\_  
\_\_\_\_\_

2. How, specifically, is the report being used? (Information source, design data, procedure, source of ideas, etc.) \_\_\_\_\_  
\_\_\_\_\_  
\_\_\_\_\_

3. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. \_\_\_\_\_  
\_\_\_\_\_  
\_\_\_\_\_

4. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) \_\_\_\_\_  
\_\_\_\_\_  
\_\_\_\_\_

BRL Report Number BRL-TR-3283 Division Symbol \_\_\_\_\_

Check here if desire to be removed from distribution list. \_\_\_\_\_

Check here for address change. \_\_\_\_\_

Current address:      Organization \_\_\_\_\_  
   Address \_\_\_\_\_  
   \_\_\_\_\_  
   \_\_\_\_\_

### DEPARTMENT OF THE ARMY

Director  
U.S. Army Ballistic Research Laboratory  
ATTN: SLCBR-DD-T  
Aberdeen Proving Ground, MD 21005-5066

OFFICIAL BUSINESS

**BUSINESS REPLY MAIL**

FIRST CLASS PERMIT No 0001, APG, MD

Postage will be paid by addressee.

Director  
U.S. Army Ballistic Research Laboratory  
ATTN: SLCBR-DD-T  
Aberdeen Proving Ground, MD 21005-5066

NO POSTAGE  
NECESSARY  
IF MAILED  
IN THE  
UNITED STATES